

NovaLiner® 16

7.2 OZ GEOMEMBRANE



NOVA LINER

PRODUCT DESCRIPTION

A medium weight fabric incorporating a new coating recipe designed to improve toughness and abrasion resistance.

RECOMMENDED APPLICATIONS

Interim Landfill Covers, Liners, Misc. Covers

PRODUCT DIMENSIONS

Cores 4 inch I.D. or 5 inch I.D. available (10 cm or 13 cm)
Width Up to 150 in (381 cm) (-0, +0.5) as ordered

Length Minimum 250 yds/roll (229 m); up to 1000 yds/roll (914 m)

PRODUCT SPECIFICATIONS

Weave Woven black HDPE scrim

Coating LDPE, 2.5 mil average each side (59 g/m²/side) **Color** White, black or other colored coatings available

Weight $7.2 \text{ oz/yd}^2 (244 \text{ g/m}^2) \pm 5\%$



These values are typical data and are not intended as limiting specifications.



PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness	Nominal 16 mil (0.40 mm), ± 10%
ASTM D1777	14011iii ai 10 11iii (0.40 11iiii), ± 1070
Grab Tensile (N) ASTM D7004	MD 210 lb (932) TD 190 lb (844)
Strip Tensile (N/5cm) ASTM D7003	MD 135 lb/in (1199) TD 130 lb/in (1154)
Tongue Tear-large scale (N) ASTM D5884	MD 60 lb (266) TD 60 lb (266)
Mullen Burst ASTM D751	375 psi (2584 kPa)
MVTR ASTM E96 Proc. BW	0.24 g/m ² ·24hr (0.03 perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	5.42 x 10 ⁻¹⁵ cm/s
Hydrostatic Resistance ASTM D751	97 psi (668 kPa)
Puncture Resistance ASTM D4833	113 lb (502 N)
CBR Static Puncture ASTM D6241	922 lb (4094 N)
Carbon Black Content ASTM D4218	3 %
Dimensional Stability ASTM D1204	MD -2.3% TD -2.0%
Low Temperature Flex ASTM D2136	MD & TD: Pass @ -40°C (-40°F)
HP-OIT ASTM D5885 (Measured on coating formulation)	2122 minutes
Accelerated UV Weathering ⁱ ASTM G151 ASTM G154	>90% strength retention after 2000 hrs exposure @ 0.77 W/m²/nm, or 1200 hrs exposure @ 1.35 W/m²/nm

MD = Machine Direction. TD = Transverse Direction. ⁱ Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4 hrs condensation @ 50°C









These values are typical data and are not intended as limiting specifications.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

