DCT102A PREMIUM GRADE DOUBLE-COATED TISSUE TAPE

DESCRIPTION

Tissue paper coated both sides with an aggressive pressure-sensitive acrylic adhesive that is engineered to bond to almost any surface. Features a 60# poly-coated kraft paper liner (white).

PRODUCT APPLICATIONS

Core starting, splicing paper and film, mounting and many other generalpurpose applications that requires the joining of two surfaces. Tissue carrier is hand tear-able. Intended for permanent application. Product is not repulpable.

ADHESVE CERTIFICATION

Photographic activity test (PAT), per ISO 18916.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/11

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	10# Tissue
Adhesive	Solvent Acrylic
Adhesion to Steel (oz/in of width) PSTC-101	69 (18.9 N/25mm)
Quick Stick to Steel (oz/in of width) PSTC-5	28 (7.6 N/25mm)
Shear Adhesion to Steel (minutes) (1" x 1" x 1000g @ 23°C (73°F)	>10,000
Shear Adhesion to Steel (minutes) (1" x 1" x 500g @ 60°C (140°F)	> 6000
Temperature Resistance (short term) Temperature Resistance (long term)	+250°F (121°C) +140°F (60°C)
Total Thickness w/ liner (mils)	8.3 (0.21 mm)
Total Thickness w/o liner (mils) PSTC-133	3.8 (0.10 mm)
Liner Type / Thickness (mils) PSTC-133	PCK – White 4.5 (0.11 mm)
Color	White

