P2960

DOUBLE-COATED PET FILM

INTERTAPE POLYMER GROUP®

TECHNICAL DATA SHEET

DESCRIPTION

1.0 mil polyester (PET) film coated on both sides with pressure-sensitive acrylic adhesive Provides good initial tack allowing immediate/ permanent bond to a variety of surfaces (including irregular, LSE (such as PE, PU or PP) and porous surfaces. Features an easy release 6 mil PCK liner 80# (white).

Product is not repulpable.

PRODUCT APPLICATION

Ideal for graphic overlays, nameplates, appliques and other industrial applications such as bonding, fixing, mounting and splicing that requires the joining of two surfaces.

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing 1.0 mil (25µ) PET film

Adhesive Solvent Acrylic

Adhesion to Steel (oz/in of width) 74 (2.1 kg/25mm)

PSTC-101

Total Thickness w/o Liner (mils) 6.3 (0.16mm)

PSTC-133

Shear Adhesion to Steel (hours) >24

25mm x 25mm x 1 kg @ 77°F (25°C)

PSTC-107

Service Temperature -22°F to +212°F

(-30°C to +100°C)

Color Clear



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

EFFECTIVE: 03/16

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or





