

202 Flex*Pro*°



ALTERNATIVE TO FOIL TAPE





Please note:

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness.

The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded.

No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

FLEXPRO® FLEXIBLE DUCT TAPE

DESCRIPTION

This tape is made of a special UV resistant treated polypropylene film and coated with a high shear, high tack acrylic adhesive. The 202 meets UL & CAN/ULC requirements as a closure system for flexible air ducts and air connectors.

MAIN FEATURES

- Excellent alternative to aluminum foil tape. No liner makes it easier and faster to use and delivers a tighter seal due to the elongation characteristic of the film.
- UL-181B-FX and CAN/ULC-S102 listed.
- Meets CAN/ULC-S109 standard.
- Strong holding power, provides permanent bond.
- Resistant to UV, mold, moisture, flame spread and smoke generation.
- Can be torn by hand.

APPLICATIONS

- Sealing of flexible air ducts and air connectors.
- Sealing of foam insulation used for water pipes.

TECHNICAL DATA

| Colour | Black, Silver |
|--|---------------------------------|
| Backing | U.V. Treated Polypropylene Film |
| Adhesive | |
| Thickness | |
| Adhesion to steel | 40 oz/in |
| Tensile strength | |
| Elongation | 140% |
| Application Temperature | 10°C (14°F) / 50°C (122°F) |
| Temperature Resistance | 40°C (-40°F) / 100°C (212°F) |
| VOC (Volatile Organic Compound) content | Estimated 0,1% |
| Moisture Vapor Transmission Rate | 3.9x10-9 g/Pa s m² |
| (Test in accordance with ASTM E 96-00e1) | |
| Water Penetration Rate | 0.009 g/100 in ² |
| | |
| Air Permeance Rate | 0.0010 L/s m² |
| | |