### **3 OZ (1.5 mil) FIBC** UNCOATED FLEXIBLE INTERMEDIATE BULK CONTAINER

#### DESCRIPTION

NovaThene<sup>®</sup> brand 3.0 oz (1.5 mil), white, uncoated flexible intermediate bulk container.

#### FABRIC SPECIFICATIONS

Weave:Woven natural PP scrimCoating:1.5 mil average, one side<br/>(35 g/m² average per side)Weight:3.7 oz/yd² (125 g/m²) +/- 5 %

#### **ROLL SPECIFICATIONS**

Cores:	4 inch I.D.
Width:	36" (0.9144 m), 42" (1.067 m),
	48" (1.219 m)
Length:	Minimum 600 yds/roll; (549 m)

# These values are typical data and are not intended as limiting specifications.

FDA Status – This fabric complies with Title CFR Parts 177.1520 and 178.2010.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Technical Service (Canada): 800.565.4533 Technical Service (US): 800.565.1450

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 6/14

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

#### **PERFORMANCE PROPERTIES**

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Grab Tensile ASTM D5034

Trapezoidal Tear ASTM D4533 Warp 50 lb, 222 N / Weft 65 lb, 289 N

Warp 165 lb, 734 N / Weft 190 lb, 845 N

ASTM D4533 Mullen Burst

300 psi / 2070 kPa

Accelerated UV Weathering<sup>1</sup>

ASTM D3786

ASTM G154

>70% strength retention after 2000 hrs Exposure @ 0.77 W/m²/nm, or 1200 hrs Exposure @ 1.35 W/m²/nm.

<sup>1</sup> Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50°C

