# **6.0 (2 mil) FIBC**

## COATED FLEXIBLE INTERMEDIATE BUI K

### INTERTAPE POLYMER GROUP®

## **TECHNICAL DATA SHEET**

#### **DESCRIPTION**

NovaThene® brand 6.0 oz (2 mil), white, uncoated flexible intermediate bulk container.

#### **FABRIC SPECIFICATIONS**

Weave: Woven natural PP scrim using

UV stabilized tapes

Coating: 2.0 mil average both sides

(47 g/m<sup>2</sup> both side)

Color: clear coating

Uncoated 6.4 oz/yd<sup>2</sup> (217g/m<sup>2</sup>) Weight:

+/- 5%

Coated 9.2 oz/yd2 (312g/m2)

+/- 5%

#### **ROLL SPECIFICATIONS**

4 inch I.D. (101.6 mm) Cores:

available

Width: 36" (914cm), 42" (1067cm),

48" (1219cm)

Minimum 600 yds/roll (549 m) Length:

These values are typical data and are not intended as limiting specifications.

# intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273 Technical Service (Canada): 800.565.4533 Technical Service (US): 800.565.1450 www.itape.com | info@itape.com

#### PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

**Grab Tensile** Warp 450 lb 1998 N / Weft 435 lb 1931 N ASTM D5034

**Trapezoidal Tear** 

Warp 145 lb 643 N / Weft 140 lb 621 N **ASTM D4533** 

**Tonque Tear** Warp 130 lb 577 N / Weft 110 lb 488 N **ASTM D2261** 

**Mullen Burst** 810 psi / 5580 kPa

**ASTM D3786** 

**Temperature Range** -20 to 80°C, -4 to 176°F

**Accelerated UV** >70 % strength retention after 1200 hrs Weathering<sup>1</sup> exposure @ 0.77 W/m<sup>2</sup>/nm

ASTM G154

<sup>1</sup> Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50°C

Physical tests are based on coated fabrics.

FDA Status - This fabric complies with Title CFR Parts 177.1520 and 178.2010.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 6/14

