

RP3

#274 PET MEDIUM GRADE FILAMENT TAPE

DESCRIPTION

Uni-directional polyester (PET) film strapping tape with reinforcements and a pressure-sensitive natural rubber adhesive. High tensile strength; high adhesion and impact strength.

PRODUCT APPLICATION

High impact resistance for packaging and holding. Particularly useful for palletizing and bundling pipes of various types. Also used for steel coil tabbing; bundling of tubes, conduit, rods, and skis.

GOVERNMENT COMPLIANCE

ASTM D5330, Type I

STORAGE RECOMMENDATION

Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE

When stored under recommended conditions, converted rolls have an expected shelf life of up to one year from date of manufacture. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within 6 months of date of shipment.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 11/13

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	1.42 mil (0.036 mm) Polyester Film
Adhesive	Natural Rubber / Resin
Reinforcement	Polyester
Adhesion to Steel (oz/in of width) (at 90° peel angle) ASTM D3330	38 (10.4 N/25mm)
Tensile Strength (lbs/in of width) ASTM D3759	274 (1200 N/25mm)
Elongation (% at break) ASTM D3759	20
Total Thickness (mils) PSTC-133	9.2 (0.233 mm)
Quick Stick (oz/in of width) To Kraft To Steel	3.4 (1.1 N/25mm) 29 (7.9 N/25mm)
Color	Natural

