PS8

HIGH TEMP PREMIUM PAPER FLATBACK TAPE

INTERTAPE POLYMER GROUP®

TECHNICAL DATA SHEET

DESCRIPTION

Strong, natural colored kraft flatback paper with temperature resistant acrylic adhesive. Product is not repulpable. Temperature resistant.

PRODUCT APPLICATION

For splicing of light floor covering and similar materials during manufacturing. Also for leasing / beaming synthetic fibers.

STORAGE RECOMMENDATION

Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE

When stored under recommended conditions, converted rolls have an expected shelf life of up to eight (8) months from the date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within six (6) months of date of shipment.

intertape polymer group

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or ourantese for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 03/17

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing		Kraft Flatback
Adhesive		Solvent Acrylic
Tensile Strength (lbs/in of width) ASTM D-3759	MD CD	54 (236 N/25mm) 32 (140 N/25mm)
Elongation (% at break) ASTM D-3759		4
Adhesion to Steel (oz/in width) ASTM D-3330		54 (15 N/25 mm)
Total Thickness (mil) ASTM D-3652		9.1 (0.23 mm)
Operating Temperature Range		+40°F ~ +350°F (4°C ~ +176°C)
Color		Beige

