PE35 POLYETHYLENE FILM TAPE

DESCRIPTION

Durable, moisture resistant polyethylene (PE) film backing with a synthetic rubberbased pressure-sensitive adhesive. Bonds well to a variety of surfaces. This tape is designed to offer a high degree of conformability without excessive stretch. Stiffer backing makes it easier to handle in certain applications.

PRODUCT APPLICATION

For patching, sealing, bundling and wrapping. For splicing and surface protection. Vapor barrier seaming, wire hold down, multi-purpose convention applications, short term masking for EIFS and holding poly sheeting barrier film.

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Polyethylene (PE) Film
Adhesive	Synthetic Rubber
Adhesion to Steel (oz./in of width) ASTM D-3330	75 (20.5 N/25mm)
Tensile Strength (Ibs./in of width) ASTM D-3759	23 (100.7 N/25mm)
Elongation (% at break) ASTM D-3759	75
Total Thickness (mils) ASTM D-3652	7.0 (0.178mm)
Application Temperature Range	+45°F to +150°F (+7°C ~ +65°C)
Operating Temperature Range	+20°F ~ +200°F (-7°C ~ +93°C)
Colors	Multiple



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



