# **Poly Masking Tape**

### STUCCO MASKING TAPE

## DESCRIPTION

Poly masking tape is based on durable, moisture resistant PE (polyethylene) backing with a rubber-based pressure-sensitive adhesive that bonds well to most surfaces. Designed to offer a high degree of conformability without excessive stretch. Easy tear edges for ease of application. UV resistant and performs well over a wide range of temperature (including cold) conditions.

### **PRODUCT APPLICATIONS**

Preferred for use in exterior insulation and finish systems (EIFS) and as masking during stucco application. Can also be used for splicing PE films and surface protection.

# ipg intertape polymer group™

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/18

## INTERTAPE POLYMER GROUP®

# **TECHNICAL DATA SHEET**

### **NOMINAL VALUES**

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

**Backing** PE

**Adhesive** Synthetic Rubber

**Tensile Strength** (lbs./in. of width) 23 (100.7 N/25mm)

**Adhesion to Steel** (oz./in. of width) 85 (23.3 N/25mm)

**Elongation** (% at break) 75

**Total Thickness** (mils) 7.5 (0.19mm)

**Color** Red

### **Suggested Temperature Resistance**

Operating Temp. Range: +32°F to +160°F

(0°C to +71°C)

Application Temp. Range: +45°F to +120°F

(+7°C to +49°C)

Best results when applied at +65°F (+18°C)

