## **RB6-6** LIGHT DEPRIVATION TARP

## **PRODUCT DESCRIPTION**

The 12mil Light Deprivation Tarp is a medium weight opaque woven fabric for use in greenhouse applications where light control is important, such as light deprivation coverings.

#### **FABRIC SPECIFICATIONS**

Weave: Woven black HDPE scrim
Coating: 1.75 mil average each side (42 g/m<sup>2</sup>/side)
Color: Black/White
Weight: 5.2 oz/yd<sup>2</sup> (176 g/m<sup>2</sup>)

#### **ROLL SPECIFICATIONS**

Cores: 4 inch (101.6 mm) or 5 inch (127 mm) I.D. available Width: Up to 144 inches (-0, +0.5) as ordered, 3.66 (-0, +12 mm) Length: minimum 500 yds/roll (457m); up to 2000 yds/roll (1829m)

These values are typical data and are not intended as limiting specifications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.565.2000

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Cur standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 03/17

# INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

## PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. These data should not be considered specification.

**Grab Tensile** ASTM D5034

Warp 180 lb 800 N / Weft 125 lb 555 N

Tongue Tear

Warp 50 lb, 222 N / Weft 50 lb, 222 N

ASTM D2261

275 psi / 1894 kPa

exposure @ 1.35 W/m²/nm.

Mullen Burst ASTM D3786

Accelerated UV Weathering<sup>i</sup> ASTM G154 >90 % strength retention after 2000 hrs exposure @ 0.77 W/m²/nm, or 1200 hrs

<sup>i</sup> Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50°C

