RU8-6 200 MEMBRANE STRUCTURE FABRIC

DESCRIPTION

NovaShield[®] RU8-6 200 is a mediumweight fabric woven from highly stabilized clear HDPE tapes with LDPE coating. For use in greenhouses, portable garages and utility sheds.

FABRIC SPECIFICATIONS

Weave:	Woven clear HDPE scrim		
Coating:	1.75 mil average both sides		
	(41 g/m ² average per side)		
Color:	Clear and colored coatings		
	available		
Weight:	6.0 oz/yd ² (203 g/m ²) +/- 5 %		

ROLL SPECIFICATIONS

Cores: 4 inch I.D. or 5 inch I.D. available Width: Up to 144 inches (-0, +0.5) as ordered Length: Minimum 500 yds/roll; up to 1000 yds/roll

These values are typical data and are not intended as limiting specifications.



intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.565.2000

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 1/15

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

	Grab Tensile ASTM D5034	Warp 220 lb, 977 N / Weft 175 lb, 777 N		
Tongue Tear ASTM D2261		Warp 65 lb, 288 N / Weft 65 lb, 288 N		
	Trapezoidal Tear ASTM D4533	Warp 65 lb, 288 N / Weft 75 lb, 333 N 370 psi / 2549 kPa		
	Mullen Burst ASTM D3786			
	Accelerated UV Weathering ¹ ASTM G154	>80% strength retention after 2000 hrs exposure @ 0.77 W/m²/nm, or 1200 hrs exposure @ 1.35 W/m²/nm.		
	Light Transmittance on clear/clear ASTM E903	Solar UV Visible	73.3% 66.5% 72.2%	

¹ Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50°C

75.0%

NIR

