

Fragile Tape

PRINTED 260 REINFORCED WATER-ACTIVATED TAPE

DESCRIPTION

3-way fiberglass reinforced natural kraft carton sealing tape manufactured with water-activated adhesive.

PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads.

ADHESION (WATER AT RECOMMENDED 110°F/43°C)

| | |
|----------|-----------|
| Fipago | |
| 2/0 | 44 mm-kgf |
| 2/1 | 66 mm-kgf |
| 5/0 | 70 mm-kgf |
| 15/0 | 86 mm-kgf |
| McLaurin | 86 |

STORAGE RECOMMENDATION

Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE

When stored under recommended conditions, converted rolls have an expected shelf life of up to two years from date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within 6 months of date of shipment.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 08/24

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on ASTM and other standard tests. This data should not be considered specification.

PHYSICAL PROPERTIES

| | |
|------------|------------------------|
| Caliper | 7.0 mils (0.18mm) |
| MD Tensile | 70 lbs/in (311 N/25mm) |
| CD Tensile | 30 lbs/in (131 N/25mm) |

Recommended for use on average weight cartons up to 55 pounds (25 kg).

CONSTRUCTION PER 3,000 SQUARE FEET (metric)

| | |
|---------|---|
| Top Ply | 25 lb (41 g/m ²) Natural Kraft Paper |
|---------|---|

| | |
|------------|---|
| Bottom Ply | 25 lb (41 g/m ²) Natural Kraft Paper |
|------------|---|

| | |
|---------------------|----------|
| Laminating Adhesive | Hot Melt |
|---------------------|----------|

| | |
|--------------------------|-----------------|
| Water-Activated Adhesive | Modified Starch |
|--------------------------|-----------------|

| | |
|------------------|--|
| MD Reinforcement | (2-1-1-1-2) 75 Fiberglass (per 3"), ½" spacing |
|------------------|--|

| | |
|------------------|--|
| CD Reinforcement | (1-1-1) 150 Fiberglass, 1.10" spacing, 43 degree angle |
|------------------|--|

