

BRAND

TECHNICAL DATA SHEET

INTERTAPE POLYMER GROUP®

FRU ELITE

DESCRIPTION

NovaShield® FRU ELITE is a heavyweight fabric for applications requiring flame retardants and UV stability, such as membrane structures. This ELITE product is manufactured with a high strength film laminated to one side and a proprietary coating on the back side. This high strength film is used to enhance abrasion resistance, flex resistance, seam strength, UV resistance and longevity. The scrim is produced in a special weaving pattern to enhance flatness, abrasion resistance, and tear properties.

FABRIC SPECIFICATIONS

Weave: Woven HDPE scrim using natural

FR/UV tapes

Coating: White flame retardant PE Film: White flame retardant PE

Colour: White FRU only

Weight: 13.75 oz/yd² (466g/m²) +/- 5 %

ROLL SPECIFICATIONS

Cores: 4 inch I.D. or 5 inch I.D. available

Width: 144 inches (-0, +0.5) Length: White/white – 500 yards

These values are typical data and are not intended as limiting specifications.

intertape polymer group®

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273

www.itape.com | info@itape.com

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. These data should not be considered a specification.

Grab Tensile Warp 430 lb 1909 N / Weft 400 lb 1776 N

ASTM D5034

Strip Tensile (N/5cm) Warp 265 lb/in (2353)/Weft 250 lb/in (2220)

ASTM D5035

Tongue Tear Warp 100 lb 444 N / Weft 90 lb 400 N

ASTM D2261

Trapezoidal Tear Warp 85 lb 377 N / Weft 85 lb 377 N

ASTM D4533

Mullen Burst 665 psi / 4582 kPa

ASTM D3786

Accelerated UV 100% strength retention after 2000 hrs **Weathering**¹ exposure @ 0.77 W/m²/nm, or 1200 hrs

ASTM G154 exposure @ 1.35 W/m²/nm

Low Temperature Bend -65°C

ASTM D2136

FR PERFORMANCE

This product meets the requirements of NFPA 701 – 2015 (Methods 1 and 2), ASTM E84 -16 (Class 1), CAN/ULC S102-10, CAN/ULC S109-14 (Small and Large Flame tests)

20-year Prorated Warranty – Please see your territory manager for details.

¹ Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4hrs condensation @ 50°C

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/23

