



## Exfilmplus® SHIELD

OPAQUE SHRINK FILM

IPG's new Exfilmplus® SHIELD is a polyolefin shrink film designed to conceal the contents of wrapped products. This heavy-duty film can be used to replace expensive corrugated containers.

### SUSTAINABILITY

- Contains certified post-industrial recycled content
- Qualified for the How2Recycle store drop-off label
- Made in a certified zero waste facility
- Cradle to Cradle Certified® Silver

### FEATURES & BENEFITS

- Fully opaque gray film maintains the confidentiality of sensitive documents and high dollar products
- Eliminates the corrugated container and void fill when packaging items strong enough to withstand the rigors of shipping
- Designed for fulfillment houses and e-commerce shippers delivering product to the consumer
- High speed pack off for improved output rates and lower labor costs
- Crosslinked Technology provides consistent sealing and shrinking
- Printable for enhanced marketing opportunities



Box and void fill add to the packaging and dim weight costs of each item shipped.

VS.



The same product packaged in Exfilmplus® SHIELD reduces packaging and dim weight shipping costs.

### PRODUCT APPLICATIONS

- Wrapping of confidential items such as insurance policies, annual reports and other sensitive documents and deliveries
- Concealment of high dollar products, eg. high-end auto components, electronics or jewelry
- Packaging of items that can withstand the rigors of shipping without the corrugated container, eg. shoes

## PRODUCT ATTRIBUTES

CHARACTERISTICS	TEST METHOD	REPRESENTATIVE VALUES			
		GRAY		GRAY	
<b>Gauge</b>		150		100	
<b>Roll Length - Center Fold</b>		1,750		2,625	
<b>Roll Length - Single Wound</b>		3,500		5,250	
<b>Post Industrial Recycled Content</b> (not less than %)		25		25	
<b>Low Temperature Usage</b> (°F)		-45°		-45°	
<b>Shrink Temperature</b> (°F)		240 - 340°		240 - 340°	
<b>Max. Storage Temp.</b> (°F) 2 years max.		90°		90°	
<b>Transmittance %</b>	D1003	2.5		5.5	
<b>Gloss at 20°</b>	D2457	68		60	
<b>Coefficient of Friction</b> (film to film), kinetic	D1894	0.12		0.17	
<b>Oxygen Transmission Rate</b> (cc / 100 in <sup>2</sup> / 24 hrs.)	D3985	265		421	
<b>Water Vapor Transmission Rate</b> (g / 100 in <sup>2</sup> / 24 hrs.)	F1249	0.19		0.32	
		MD	TD	MD	TD
<b>Tensile Strength</b> (PSI)	D882	14,000	14,000	14,000	14,000
<b>Elongation at Break</b> (%)	D882	155	145	150	140
<b>Stiffness Modulus</b> (PSI)	D882	35,000	45,000	47,000	50,000
<b>Unrestrained Shrink (%) @ 250°F</b>	D2732	63	63	65	65
<b>Tear Propagation</b> (g / ply)	D1922	35	35	23	23

These values are typical data and are not intended as limiting specifications.

## IPG SUSTAINABLE ACHIEVEMENTS AND FOOD GRADE CERTIFICATIONS



Certifications and achievements are product and manufacturing plant specific.



Scan for more info or visit [itape.com/shrink](http://itape.com/shrink)

