## **Stretch Film**

Genesys<sup>®</sup> Ultra Plus H7 (High Performance Machine Grade)

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

Test	Values (listed by film thickness)				
	Reference Methods	37 gauge 9.4 micron 0.37 mil	41 gauge 10.4 micron 0.41 mil	45 gauge 11.4 micron 0.45 mil	48 gauge 12.1 micron 0.48 mil
<b>Ultimate Tensile MD</b> (psi)	ASTM D882	7254	7762	8270	8650
<b>Ultimate Tensile TD</b> (psi)	ASTM D882	5195	5421	5646	5815
Elongation MD (%)	ASTM D882	520	560	600	630
Elongation TD (%)	ASTM D882	738	753	768	779
Tear Resistance MD (grams and g/mil)	ASTM D1922	146 grams 396 g/mil	167 grams 408 g/mil	189 grams 419 g/mil	204 grams 426 g/mil
Tear Resistance TD (grams and g/mil)	ASTM D1922	443 grams 1197 g/mil	479 grams 1167 g/mil	514 grams 1143 g/mil	541 grams 1127 g/mil
Dart Drop (grams and g/mil)	ASTM D1709	75 grams 204 g/mil	77 grams 188 g/mil	79 grams 176 g/mil	80 grams 167 g/mil
Pre-stretch (% at break)	IPG/Highlight	370	385	400	415
<b>Cling</b> (in to out, grams at 200% pre-stretch)	IPG method	44 grams	44 grams	44 grams	44 grams

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com



EFFECTIVE: 10/27/22