

ProMask Blue®

HIGH PERFORMANCE BLUE PAINTER'S MASKING TAPE

DESCRIPTION

Conformable crepe paper masking tape with pressure-sensitive synthetic rubber adhesive. Secure adhesion and clean removal from most surfaces. Resistant to U.V. (up to 14 days), humidity and paint bleed-through.

PRODUCT APPLICATION

For interior masking wherever tape (adhesive) will be exposed to sunlight. Compatible with polyurethane coated surfaces, wallpaper, new, or freshly painted wallboard.

STORAGE RECOMMENDATION

Store new stock behind current stock. Store in a clean, dry place. Temperature of 70°F (21°C) +/- 6°F, and 40% to 50% relative humidity are recommended.

SHELF LIFE

When stored under recommended conditions, converted rolls have an expected shelf life of up to one (1) year from the date of shipment. Jumbo rolls have the same expected shelf life, but it is recommended that they are converted within six (6) months of date of shipment.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA

Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 02/26

IPG®

TECHNICAL DATA SHEET

NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Coarse Crepe Paper
Adhesive	Synthetic Rubber
Tensile Strength (lbs/in) ASTM D3759	22 (96 N/25mm)
Elongation (% at break) ASTM D3759	8
Adhesion to Steel (oz/in) ASTM D3330	25 (6.8 N/25mm)
Total Thickness (mil) ASTM D3652	5.8 (0.147mm)
Temperature Resistance	40°F to 120°F (4.4°C to 49°C)

